

ACEROS PARA TRABAJO EN FRÍO

Formatos disponibles

Productos largos*

Chapas

*) Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Descripción

BÖHLER K340 ISODUR es un acero para herramientas de trabajo en frío con 8% de Cromo, fabricado mediante el proceso ESR de refundición bajo electroescoria. Esta tecnología desarrollada y probada por BÖHLER garantiza cantidades mínimas de micro y macrosegregaciones, lo cual nos permite ofrecerle el acero de la mayor pureza y homogeneidad, necesarios para lograr las características que aseguren su rendimiento.

Método de obtención

Airmelted + Remelted

Propiedades

- > Dureza y Ductilidad : buena
- > Resistencia al desgaste : alto
- > Resistencia a la compresión : buena
- > Estabilidad dimensional : buena
- > Afilabilidad : muy alta

Aplicaciones

- > Cuchillas de máquinas (fabricantes)
- > Acuñado
- > Tornillos y cilindros
- > Rodillos
- > Thread rolling (ES)
- > Laminación
- > Corte fino / Troquelado / Estampado
- > Componentes para la industria del reciclaje
- > Componentes de desgaste
- > Pill punching dies
- > Conformado en frío
- > Compactación de polvo
- > Componentes para equipos bajo tierra (perforación, ejes, etc.)
- > Componentes generales de ingeniería mecánica
- > Glasfibre reinforced plastics

Composición Química

C	Si	Mn	Cr	Mo	V	Al	Nb
1,10	0,90	0,40	8,30	2,10	0,50	+	+

Características

	Resistencia a la compresión	Estabilidad dimensional durante el tratamiento térmico	Tenacidad	Resistencia al desgaste abrasivo	Resistencia al desgaste adhesivo
BÖHLER K340 ISODUR®	★★★	★★★★	★★★	★★★	★★★★
BÖHLER K100	★★	★★	★	★★★	★★
BÖHLER K105	★★	★★	★	★★	★★
BÖHLER K107	★★	★★	★	★★★	★★
BÖHLER K110	★★	★★★	★	★★★	★★
BÖHLER K190 MICROCLEAN®	★★★★	★★★★★	★★★★	★★★★	★★★★
BÖHLER K294 MICROCLEAN®	★★★★★	★★★★★	★★★	★★★★★	★★★★★
BÖHLER K340 ECOSTAR®	★★★	★★★	★★	★★	★★
BÖHLER K346	★★★	★★★	★★★	★★★★	★★
BÖHLER K353	★★	★★★	★★	★★	★★
BÖHLER K360 ISODUR®	★★★	★★★★	★★★	★★★★	★★★★
BÖHLER K390 MICROCLEAN®	★★★★★	★★★★★	★★★★	★★★★★	★★★★★
BÖHLER K490 MICROCLEAN®	★★★★	★★★★★	★★★★	★★★★	★★★★
BÖHLER K497 MICROCLEAN®	★★★★★	★★★★★	★★★	★★★★★	★★★★★
BÖHLER K888 MATRIX	★★★	★★★★★	★★★★★	★★	★★
BÖHLER K890 MICROCLEAN®	★★★★	★★★★★	★★★★★	★★★	★★★

Estado de suministro

recocido

Dureza (HB)	máx. 235
-------------	----------

Tratamiento térmico


Alivio de tensiones

Temperatura	650 °C	After through heating, hold in neutral atmosphere for 1-2 hours. Slow cooling in furnace Intended to relieve stresses caused by extensive machining or in complex shapes.
-------------	--------	---

Temple y revenido

Temperatura	1.040 a 1.060 °C	Quenching: Oil, salt bath, compressed air, air, gas. Holding time after temperature equalization: 15 to 30 minutes. After hardening, tempering to the desired working hardness according to the tempering chart.
-------------	------------------	--

Tempering chart



Specimen size: square 20 mm (0,787 inch)

Slow heating to tempering temperature immediately after hardening.

Time in furnace 1 hour for each 20 mm (0,787 inch) of workpiece thickness but at least 2 hours.

Please refer to the tempering chart for guide values for the achievable hardness after tempering.


It is recommended to temper at least three times above the secondary hardness maximum.

Cooling in air to room temperature after each tempering step is recommended.

Tempering for stress relieving 30 to 50 °C (86 to 122 °F) below the highest tempering temperature.

Recommended tempering temperature range is indicated by the blue area in the chart.

CCT chart for continuous cooling



Austenitising temperature: 1060 °C (1940 °F)
Holding time: 30 minutes


O Vickers hardness

8...100 phase percentages

0.3...180 cooling parameter λ , i.e. duration of cooling from 800 to 500 °C (1472 to 932 °F) in $s \times 10^{-2}$

A... Austenite
K... Carbide
P... Pearlite
RA... Residual austenite
M... Martensite
Ms... Martensite starting temperature

Quantitative phase diagram



Propiedades físicas

Temperatura (°C)	20
Densidad (kg/dm ³)	7,68
Conductividad térmica (W/(m.K))	17,8
Calor específico (kJ/kg K)	0,49
Resistencia eléctrica específica (Ohm.mm ² /m)	0,64
Módulo de elasticidad (10 ³ N/mm ²)	206

Expansión térmica

Temperatura (°C)	100	200	300	400	500	600	700
Expansión térmica (10 ⁻⁶ m/(m.K))	11,2	11,8	12,3	12,7	12,9	13,1	13,1

Long Products: For additional specifications and technical requirements, please contact our regional voestalpine BÖHLER sales companies.

Sheet & Plates: Product Variant may differ in terms of melting process, technical data, delivery, and surface condition as well as available product dimensions. Please contact voestalpine BÖHLER Bleche GmbH & Co KG.

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG
Mariazeller Straße 25
8605 Kapfenberg, AT
T. +43/50304/20-0
E. info@bohler-edelstahl.at
<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine
ONE STEP AHEAD.